
Target Values: Candesce® C1S Paperboard (Idaho)

English (mils, lbs/3msf)	nominal	10-129	12-143	14-163	15-172	16-182	17-190	18-199	20-217	22-233	24-250	26-273
Metric (µm, g/sq m)	nominal	254-210	305-233	356-266	381-280	406-297	432-309	457-324	508-354	559-380	610-408	660-444
Basis Weight	lbs/3msf	129	143	163	172	182	190	199	217	233	250	273
Brightness	GE	88	88	88	88	88	88	88	88	88	88	88
Caliper	mils	10	12	14	15	16	17	18	20	22	24	26
Coated b* Color	Spectro	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Coated Smoothness	Sheffield	8	10	12	13	14	15	16	16	17	18	20
Gloss	75	53	53	53	53	53	53	53	53	53	53	53
Parker Print	microns	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
Plybond	lbs/in ²	56	56	47	47	47	47	43	43	43	43	43
Stiffness - CD	Taber g-cm	24	36	56	70	82	90	115	145	190	225	270

Stiffness values represent end-of-machine testing.

Specifications Revision Date: January 2011.

These values may change.
